
















Dyeing Colour Sample	Names of Acid Dyes	Dyeing depth (% o. w. f.)	C. I. No. (Acid)	Fastness Properties (Change of Shade)				
				Light (Xenon) 1 : 1 standard depth	Washing 40°C	Dry cleaning	Hot Pressing	Perspiration
	Flavine G 120%	1.0	Y 17	6	4-5	4-5	4-5	3
	Yellow N 200%	1.0	Y 23	4	2	-	-	4-5
	Golden Yellow G 120%	1.0	Y 36	3-4	4-5	4-5	4-5	3-4
	Yellow MR 150%	0.8	Y 42	3-4	4-5	4-5	4-5	4-5
	Yellow GR 200%	1.0	Y 49	6	4-5	4-5	4-5	4-5
	Light Yellow G 150%	0.8	Y 117	4-5	4-5	4-5	4-5	4-5
	Yellow LNW 200%	0.8	Y 151	5	4-5	4-5	4-5	4-5
	Yellow AGR 200%	0.8	Y 199	5	4-5	4-5	4-5	4-5
	Yellow E-3R 110%	1.0	O 3	2-3	3-4	4-5	4-5	4-5
	Orange II 100%	1.0	O 7	4	4	4-5	4-5	4
	Orange GS 100%	1.5	O 33	4-5	4-5	4-5	4	4-5
	Yellow RXL 200%	1.5	O 67	6	4-5	4-5	4-5	4-5
	Orange AGT 200%	1.0	O 116	4	4-5	4	4-5	4-5
	Orange 3G 270%	0.7	O 171	4	4-5	4-5	4-5	4-5
	Red G 140%	1.5	R 1	4-5	4-5	4-5	4-5	3

Dyeing Colour Sample	Names of Acid Mordant Dyes	Dyeing depth (% o. w. f.)	C. I. No. (Acid)	Fastness Properties (Change of Shade)			
				Light (Xenon) 1 : 1 standard depth	Washing 40°C	Dry cleaning	Hot Pressing
	Yellow GG 100%	1.0	Y 10	6	5	5	4
	Orange G 100%	1.0	O 6	6	4	4-5	4-5
	Red BN 100%	1.0	R 7	4-5	4-5	4-5	4-5
	Sky Blue B 100%	0.8	B 1	7	4-5	4-5	3-4
	Blue RRL 150%	1.0	B 9	7	4-5	4-5	4
	Green J 100%	1.0	G 4	6	4	-	-
	Brown RH 100%	1.0	Br 33	5	5	4-5	4
	Black A 100%	5.0	Bk 1	7	4-5	4-5	4-5
	Black PV 100%	5.0	Bk 9	6-7	4-5	4-5	4
	Black T 100%	5.0	Bk 11	7	4-5	4-5	4-5
	Black R 100%	5.0	Bk 17	6-7	4-5	4-5	4
							
							
							
							



**QUIMICOS Y COLORANTES
S.A DE C.V**

Dyeing Colour Sample		Names of Acid Dyes	Dyeing depth (% o. w. f.)	C. I. No. (Acid)	Fastness Properties (Change of Shade)				
					Light (Xenon) 1 : 1 standard depth	Washing 40°C	Dry cleaning	Hot Pressing	Perspiration
	Red B 100%	0.8	R 14	4-5	4-5	4	3	4	
	Red BG 100%	1.0	R 37	5-6	3	4-5	2	4	
	Rhodamine B 400%	1.0	R 52	2-3	3-4	4	2	4	
	Red A 100%	1.0	R 88	2-3	3	5	5	2-3	
	Red F-3GL 130%	1.2	R 111	5	4-5	4-5	4-5	4-5	
	Red F-RS 200%	1.0	R 114	3	4-5	4-5	4-5	4	
	Pink B 100%	1.0	R 138	3-4	4-5	4-5	5	5	
	Red F-2R 200%	1.0	R 151	4	4	-	4-5	4	
	Red BB 100%	1.0	R 154	5-6	4-5	4-5	4-5	4-5	
	Brill. Red B 125%	1.0	R 249	4-5	4	4-5	4	4	
	Rubine GP 200%	0.8	R 266	6	5	4-5	5	5	
	Red N-5BL 200%	0.8	R 299	3	4-5	4-5	4-5	4	
	Scarlet FG 100%	1.2	R 374	3-4	4-5	4-5	4-5	4-5	
	Violet 2R 170%	1.0	V 1	4-5	1	-	-	1	
	Violet FBL 180%	1.5	V 48	5-6	4-5	4-5	4-5	4-5	



**QUIMICOS Y COLORANTES
S.A DE C.V**

Dyeing Colour Sample		Names of Acid Dyes	Dyeing depth (% o. w. f.)	C. I. No. (Acid)	Fastness Properties (Change of Shade)				
					Light (Xenon) 1 : 1 standard depth	Washing 40°C	Dry cleaning	Hot Pressing	Perspiration
	Brill. Red 10B 140%	1.0	V 54	4-5	4-5	4-5	4-5	4-5	
	Bordeaux M-B 100%	1.0	V 90	6	4-5	-	4-5	4-5	
	Blue A 100%	1.0	B 7	2	4-5	5	4	3	
	Blue FG 200%	1.0	B 9	3	2	4-5	4	3	
	Blue AS 160%	1.2	B 25	5-6	3	4-5	4	3-4	
	Blue A2G 160%	0.8	B 40	4	3-4	4-5	4-5	4	
	Blue B 200%	1.3	B 45	5-6	4	4-5	4	3-4	
	Blue 2BR 200%	1.5	B 62	4-5	4-5	4-5	4-5	4	
	Brill. Blue RAW 150%	1.5	B 80	5-6	4-5	4	4-5	4-5	
	Blue 6B 350%	1.2	B 83	3	4-5	4-5	4	4-5	
	Brill. Blue G 360%	1.2	B 90	3	5	4-5	3-4	5	
	Blue R 100%	1.2	B 92	5	3-4	4-5	4	3-4	
	Ink Blue G 100%	0.8	B 93	2	1	4	4	2	
	Blue 7BF 100%	1.0	B 100	3	4-5	-	4	4	
	Navy Blue 5R 120%	0.5	B 113	3-4	4	4-5	4-5	4-5	



**QUIMICOS Y COLORANTES
S.A DE C.V**

Dyeing Colour Sample	Names of Acid Dyes	Dyeing depth (% o. w. f.)	C. I. No. (Acid)	Fastness Properties (Change of Shade)				
				Light (Xenon) 1 : 1 standard depth	Washing 40°C	Dry cleaning	Hot Pressing	Perspiration
	Navy Blue 5R 150%	0.5	B 113	3-4	4	4-5	4-5	4-5
	Navy Blue GR 100%	0.7	B 120	3-4	4	4-5	4-5	4-5
	Blue GAW 180%	1.2	B 127;1	5	4-5	4	4	4-5
	Blue P-R 200%	0.8	B 129	5-6	4-5	4-5	4-5	4-5
	Blue HRL 200%	1.0	B 182	6-7	3-4	-	4-5	4
	Blue BRLL 200%	1.5	B 324	4	3-4	4-5	4-5	4
	Green 5B 200%	1.2	G 9	2-3	3-4	4-5	4-5	4-5
	Dark Green B 200%	1.0	G 20	3-4	3	-	-	3
	Green GS 160%	1.0	G 25	5-6	4-5	4	4	4
	Neutral Green GK 120%	1.0	G 25	5-6	5	4	4-5	4-5
	Brown RL 200%	1.0	Br 2	3-5	4	4-5	4	4-5
	Brown R 100%	1.0	Br 14	4	4-5	-	4	4-5
	Brown B 100%	1.0	Br 75	3-4	4	4-5	4	4-5
	Brown NR 100%	1.0	Br 163	4-5	5	4-5	4	4-5
	Brown NT 100%	2.0	Br 165	4	5	4-5	4	4-5



**QUIMICOS Y COLORANTES
S.A DE C.V**

Dyeing Colour Sample	Names of Acid Dyes	Dyeing depth (% o. w. f.)	C. I. No. (Acid)	Fastness Properties (Change of Shade)				
				Light (Xenon) 1 : 1 standard depth	Washing 40°C	Dry cleaning	Hot Pressing	Perspiration
	Brown SR 100%	1.0	Br 348	4	-	-	-	-
	Brown SG 100%	1.5	Br 349	3	3	4	4	3-4
	Black ATT 100%	5.0	-	6-7	4-5	4-5	4-5	4
	Black 10B 100%	5.0	Bk 1	6-7	4-5	4-5	4-5	4
	Nigrosine WLL 100%	5.0	Bk 2	5	4	4-5	4-5	4
	Black BR 150%	5.0	Bk 24	6-7	4-5	4-5	4-5	4
	Milling Black VLG 200%	3.0	Bk 26	6-7	4	4	4-5	4-5
	Black NT 200%	3.0	Bk 29	6-7	4-5	4-5	4-5	3-4
	Chrome Black WAN 150%	5.0	Bk 52	6	4-5	4-5	4-5	4-5
	Black S-BL 140%	3.0	Bk 172	5-6	4	4-5	4	4-5
	Black M-SRL 140%	3.0	Bk 194	5-6	4	4-5	4-5	4-5
	Black 6-GNR 130%	5.0	Bk 210	3	2-3	4-5	4	4-5
	Black 6-GNR 180%	5.0	Bk 210	3	2-3	4-5	4	4-5
	Black NB-G 200%	3.0	Bk 234	3-4	3-4	4-5	4	4-5