
























































		Dyeing depth(%o.w.f.)	C.I.No. (Reactive)	Fastness				
				Light (Xenon)	Rubbing		Washing (95°C)	Perspiration
Dyeing Colour Sample	Names of Reactive Dyes		Dry		Wet	Change in shade		
	Brill. Yellow X-6G	4.0	Y-1	6-7	5	4-5	4-5	4-5
	Brill. Yellow X-7G 135%	4.0	Y-86	6-7	4-5	3-4	4-5	4-5
	Yellow X-R	4.0	Y-4	7	4-5	4	4-5	4-5
	Golden Yellow X-G	4.0	-	6-7	4-5	3-4	4-5	4-5
	Brill. Orange X-GN 140%	4.0	O-1	5-6	4-5	3	4-5	4-5
	Brill. Red X-3B 100%	4.0	R-2	5	4-5	3-4	4-5	4-5
	Brill. Red X-8B 100%	4.0	R-11	5-6	4-5	3	4-5	4-5
	Red Violet X-2R 120%	4.0	V-8	4-5	4-5	3	4-5	4-5
	Brill. Blue X-BR 140%	4.0	B-4	6-7	4-5	3	4-5	4-5
	Brill. Orange KN-5R	4.0	O-16	4-5	4-5	3	3-4	4
	Violet KN-4R	4.0	V-5	6	3-4	3-4	4	4-5
	Brill. Blue KN-R	4.0	B-19	7	4-5	3	3-4	4-5
	Brill. Blue KN-RS	4.0	B-19	6-7	4	2-3	4	4
	Turq. Blue KN-G	4.0	B-21	6	4-5	3-4	3-4	4-5
	Black KN-B	8.0	Bk-5	5-6	4	2	4	4-5

		Dyeing depth(%o.w.f.)	C.I.No. (Reactive)	Fastness				
				Light (Xenon)	Rubbing		Washing (95°C)	Perspiration
Dyeing Colour Sample	Names of Reactive Dyes		Dry		Wet	Change in shade		
	Black KN-G2RC	8.0	-	3-4	4-5	3	3-4	4-5
	Brill. Yellow KM-7G	4.0	Y-85	6-7	4-5	4	4-5	4-5
	Yellow KM-3G	4.0	-	6	4-5	4-5	4-5	4-5
	Yellow KM-RN	4.0	-	6	4-5	3-4	4-5	4-5
	Golden Yellow KM-G	4.0	Y-84	5-6	4	3	4-5	4
	Brill.Orange KM-G	4.0	O-2	5	4-5	3	5	4-5
	Brill. Orange KM-7R	4.0	-	4-5	4-5	3	4-5	4-5
	Brill.Red KM-2B	4.0	-	5-6	4-5	3	4-5	4-5
	Brill.Red KM-8B	4.0	-	5	4-5	2-3	4-5	3-4
	Blue KM-GR	4.0	-	6-7	4-5	3-4	4-5	3-4
	Turq. Blue KM-GB	4.0	B-72	6	4-5	3	3	3-4
	Brill. Yellow KE-5G	4.0	Y-135	4	4-5	3-4	3	3-4
	Brill. Yellow KE-3G	4.0	Y-81	6	4-5	3-4	4-5	4-5
	Yellow KE-4R	4.0	Y-84	5-6	4	3	4-5	4
	Brill. Orange KE-2R	4.0	O-84	3-4	4-5	3	4	5

Dyeing Colour Sample	Names of Reactive Dyes	Dyeing depth(%o.w.f.)	C.I.No. (Reactive)	Fastness				
				Light (Xenon)	Rubbing		Washing (95°C)	Perspiration
					Dry	Wet		
	Scarlet KE-3G	4.0	-	5	4-5	3	5	4-5
	Brill. Red KE-3B	4.0	R-120	5	4-5	2	4	4-5
	Brill. Red KE-7B	4.0	R-141	4	3-4	2	3-4	3-4
	Blue KE-6G	4.0	-	4-5	3	2	3	4-5
	Dark Blue KE-R	4.0	B-171	3-4	4-5	1-2	4	4
	Blue KE-GR	4.0	-	4	4	2	3-4	3
	Blue KE-GN	4.0	B-198	5	4-5	2-3	4-5	4-5
	Green KE-4BD	4.0	G-19	4	3-4	2	4	4
	Yellow M-2RE	4.0	Y-145	6	3-4	3	4-5	4-5
	Red M-3BE	4.0	R-195	4-5	3-4	2-3	4	4
	Dark Blue M-2GE	4.0	B-194	3-4	3-4	1-2	3-4	3-4

Dyeing Colour Sample	Names of Reactive Dyes	Printing Depth (g/l)	C.I.No. (Reactive)	Fastness				
				Light (Xenon)	Rubbing,		Washing (95°C)	Perspiration
					Dry	Wet		
	Brill. Yellow K-6G	40	Y-2	6-7	5	4	4-5	4-5
	Brill. Yellow K-4G	40	Y-18	6	4-5	4	4-5	4-5
	Yellow K-RN	40	Y-3	6	4-5	3-4	4-5	4-5
	Brill. Orange K-GN	40	O-5	5-6	4-5	3	4-5	4-5
	Brill. Orange K-7R	40	O-13	4-5	4-5	2-3	4-5	4-5
	Brill. Red K-2G	40	R-15	5-6	4-5	2-3	4-5	4-5
	Brill. Red K-2BP	40	R-3	6	4-5	2-3	4-5	4-5
	Violet K-3R	40	V-2	6-7	4-5	3-4	4-5	4-5
	Brill. Blue K-3R 150%	40	B-74	5-6	4-5	4	4	4
	Dark Blue K-R	40	B-13	6-7	4-5	3	4-5	4-5
	Brill. Blue K-GR	40	B-5	6	4-5	3-4	4-5	4-5
	Turq. Blue K-GL 130%	40	B-14	7	4-5	3-4	3-4	4
	Yellow Brown K-GR	40	Br-2	7	4-5	3-4	4-5	4-5
	Red Brown K-B3R	40	Br-9	4-5	4	2-3	4-5	4-5
	Black K-BR	100	Bk-8	6	4-5	2-3	4	4-5